



SATWIPES Wipes

Polyester/rayon nonwoven wipes presaturated with 70% IPA

SATWIPES SWNW0013-BPR consists of a roll of 700 saturated wipes (230 x 180mm) which are dispensed through a centre-pull container. The wipes are presaturated with 70% IPA and 30% deionised water.

The wipes are made of 50% polyester and 50% rayon nonwoven material creating a soft, durable, and clean wipe. The fabric is strong and sorbent.

Ideal when large volumes of presaturated wipes are needed for clean downs and lower grade areas.

When used as a disinfectant, the IPA wipes are efficacious against bacteria in 1 min and yeasts in 3 mins. SATWIPES wipes are authorised for sale in the EU and United Kingdom under the EU and GB Biocidal Products Regulations.



Features	Benefits
Hydroentangled polyester/rayon fabric	<ul style="list-style-type: none"> Highly sorbent with good wet strength Low in particles and fibres Excellent general purpose wipe
No binders or additives	<ul style="list-style-type: none"> Leaves no residue on the cleanroom surface
Larger number of wipes than a pouch	<ul style="list-style-type: none"> Cost effective for general applications
Resealable container	<ul style="list-style-type: none"> Maintains saturation levels throughout use and makes wipe removal easy
Presaturated wipes	<ul style="list-style-type: none"> Reduces solvent usage and VOC emissions Ensures consistent saturation of each wipe independent of the operator

Part no.	Description	Size	Packaging
SWNW0013-BPR	SATWIPES Polyester / Rayon Wipes Presaturated with 70% IPA and 30% DI Water	180 x 230mm	700 per container 2 containers per case

For more information or to request a sample, email infoeu@contecinc.com or phone +33 (0) 2 97 43 76 98

Copyright © 2023 Contec, Inc. All rights reserved. INT196 270423

Product Information	
Material and construction	Hydroentangled nonwoven 50% polyester/50% rayon
Saturant	70% IPA (USP Grade) with 30% DI water
Sterility	Nonsterile
Shelf life	2 years from manufacturing date
Environment	ISO 7 - 8 Grade C/D

Technical Data		
Attribute (units)	Typical Value	Test Method
Basis weight, nominal; (g/m ²)	42	Contec Method
Non-volatile residue, NVR		IEST-RP-CC004.3, Sec. 7.1.2
In deionized water; (g/m ²)	0.027	
In isopropyl alcohol; (g/m ²)	0.033	
Specific ions		IEST-RP-CC004.3, Sec. 7.2.2
Sodium; (ppm)	N/A	
Chloride; (ppm)	N/A	
Particles, readily releasable		
Particles ≥ 0.5µm; (x10 ⁶ /m ²)	21.3	IEST-RP-CC004.2, Sec. 5.1
Fibres > 100µm; (x 10 ³ /m ²)	0.57	IEST-RP-CC004.2, Sec. 5.2

Notes

- a) The data shown are typical values and should not be used as product specifications.
- b) Valid product comparisons may only be obtained through side-by-side testing in the same test facility, under similar conditions.
- c) Current and/or comparison data may be available. Please contact a Contec sales representative for details.

Test Methods

CTM Contec Test Method
 IEST-RP-CC004.3 Evaluating Wiping Materials Used in Cleanroom and Other Controlled Environments, Institute of Environmental Sciences and Technology, Rolling Meadows IL

Recycling Key



Efficacy Information

Test	Description	Log Reduction	Time	Test	Description	Log Reduction	Time
EN16615	<i>E. hirae</i>	>5.03	1 min	EN16615	<i>P. aeruginosa</i>	>5.09	1 min
EN16615	<i>S. aureus</i>	>5.32	1 min	EN16615	<i>C. albicans</i>	>4.06	3 min

Packaging Information

Packaging Materials					VOC Content	
	Canister	High density polyethylene (HDPE)			kg/CS	kg/PCH
	Case	Corrugated fibreboard (PAP)				
Packaging Configuration	EA/RL	RL/PCH	PCH/CS	EA/CS		
SWNW0013-BPR	700	1	2	1400	4.22	2.11
EA = Wipe, RL = Roll, PCH = Pouch, CS = Case						

Use biocides safely. Always read the label and product information before use.